



Product Type:	UV Stabilised HDPE Resin Cloth Laminate with a special solvent acrylic adhesive	
Colour:	Translucent	
Roll Size:	24mm to 1,500mm in 25m Lengths (custom lengths on request—MOQs apply)	
Adhesive:	Acrylic Solvent	
Description:	U.V. stabilised polyethylene backing with a U.V. stabilised solvent acrylic. Excellent U.V. and moisture resistance.	
Application:	Designed for the repair and strengthening of PE Hothouses. A general purpose repair tape for indoor & outdoor applications where a clear film is required, particularly suited to the joining and holding of PE sheeting. Suitable for surface protection where a high adhesion is required on stable surfaces. Commonly used in the marine industry for holding shrink film to the hull of craft.	
Technical Details:	Gauge:	0.165mm
	Tensile Strength:	63 N/cm
	Elongation at Break:	14%
	Adhesion to Steel:	7.6 N/cm
	Service Temperature:	-10°C to 60°C
	Storage Temperature:	15°C to 25°C
	Shelf Life:	12 Months
Surface Preparation:	The surface on which the tape is to be used must be clean, dry and free from grease and dust. Remember that pressure sensitive adhesive must be applied with the maximum possible pressure in order to achieve maximum adhesion levels. The recommended application temperature is between 15°C and 25°C.	
Storage:	Tapes stored below the minimum application temperature will require warming up to that level before use. Up to 24 hours may be required for this to take place.	

DISCLAIMER:

Values: All values presented have been determined by standard test methods and are average values only.

Recommendations: Whilst we are happy to recommend products from our range for applications, it is imperative that the customer/user complete their own tests to determine suitability for their application under "working conditions" and if longevity is important, that ageing tests be carried out.

Warranty: We can only warranty our products to the level that they are consistent with our Product Information Sheet values

BUT CANNOT accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.