



Product Type:	High Tack Polyethylene Surface Protection Film														
Colour:	Orange														
Roll Size:	24mm to 1530mm in 100m Lengths														
Adhesive:	Acrylic Emulsion														
Description:	Polyethylene film coated with solvent free pressure sensitive acrylic resin adhesive.														
Application:	Surface protection of "low energy" and textured surfaces. Particularly suited for plastic, glass, vinyl and veneers. Recommended for applications where a narrow width may be required. Suitable for "Mask & Peel" applications within the furniture and joinery industry e.g. kitchen benchtops, doors. Suitable for temporary outdoor masking of guttering, downpipes, balustrades etc. during rendering work.														
Technical Details:	<table><tr><td>Gauge:</td><td>0.06mm</td></tr><tr><td>Tensile Strength:</td><td>12 N/cm</td></tr><tr><td>Elongation at Break:</td><td>350%</td></tr><tr><td>Adhesion to Steel:</td><td>1.75 N/cm</td></tr><tr><td>Service Temperature:</td><td>-30°C to 50°C</td></tr><tr><td>Storage Temperature:</td><td>15°C to 25°C</td></tr><tr><td>Shelf Life:</td><td>12 Months</td></tr></table>	Gauge:	0.06mm	Tensile Strength:	12 N/cm	Elongation at Break:	350%	Adhesion to Steel:	1.75 N/cm	Service Temperature:	-30°C to 50°C	Storage Temperature:	15°C to 25°C	Shelf Life:	12 Months
Gauge:	0.06mm														
Tensile Strength:	12 N/cm														
Elongation at Break:	350%														
Adhesion to Steel:	1.75 N/cm														
Service Temperature:	-30°C to 50°C														
Storage Temperature:	15°C to 25°C														
Shelf Life:	12 Months														
Surface Preparation:	The surface on which the tape is to be used must be clean, dry and free from grease and dust. Remember that pressure sensitive adhesive must be applied with the maximum possible pressure in order to achieve maximum adhesion levels. The recommended application temperature is between 15°C and 25°C.														
Storage:	Tapes stored below the minimum application temperature will require warming up to that level before use. Up to 24 hours may be required for this to take place.														

DISCLAIMER:

Values: All values presented have been determined by standard test methods and are average values only.

Recommendations: Whilst we are happy to recommend products from our range for applications, it is imperative that the customer/user complete their own tests to determine suitability for their application under "working conditions" and if longevity is important, that ageing tests be carried out.

Warranty: We can only warranty our products to the level that they are consistent with our Product Information Sheet values

BUT CANNOT accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.